

# ProRox® SL 930<sup>SA</sup>

ProRox SL 930<sup>SA</sup> is a semi rigid stone wool slab. A one-sided facing with fibreglass reinforced aluminium foil (ALU) or glass tissue is available upon request.



## Product properties

Properties	Performance						Standard
Thermal Conductivity	T <sub>m</sub> (°C)	50	100	150	200	250	ASTM C177
	λ (W/mK)	0.039	0.047	0.054	0.064	0.075	
Nominal Density	60 kg/m <sup>3</sup>						ASTM C303
Maximum Service Temperature	450 °C						ASTM C411/C447
Linear Shrinkage	Less than 2% (at max service temperature)						ASTM C356
Reaction to Fire	EuroClass A1 Surface burning characteristics; Flame spread = passed, Smoke development = passed						EN 13501-1 ASTM E84
Chloride Content	Less than 10 ppm Conforms to the stainless steel corrosion specification as per ASTM C795						ASTM C871 ASTM C692/C871
Moisture Absorption	Less than 1% weight						ASTM C1104/ C1104M
Water Absorption	Less than 1 kg/m <sup>2</sup>						EN 1609

Note: All information and data for technical parameters are based on laboratory testing.

## Compliance

ProRox SL 930<sup>SA</sup> Slabs fully comply with the requirements as set by internationally recognized standards like, CINI 2.2.01 and ASTM C612 Type IA and IB and II.

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.

## ROCKWOOL (Thailand) Limited

WHA Eastern Industrial Estate (Map Ta Phut)  
No.1 Soi G2, Pakornsongkrohraj Road,  
Huaypong, Muang, Rayong 21150 Thailand  
T (+66) 3868 5107-110