

# Cavityrock®

Exterior insulation for cavity wall  
and rainscreen applications



## Cavityrock® Black:

Designed for open-joint cladding systems, this product is available with a bonded black mineral fiber facing to reduce installation time while providing long-term UV stability.

Rush University Medical Center, Chicago, IL

ROCKWOOL Cavityrock® is a stone wool insulation board designed for exterior cavity wall and rainscreen applications. Designed as either a mono density (<math><2.5\text{''}</math>) or dual density ( $\geq 2.5\text{''}</math>) product, Cavityrock provides improved impact resistance and conformance to wall irregularities.$

Compatible with numerous engineered cladding attachment systems, Cavityrock® is noncombustible and fire resistant, and will not develop toxic smoke or promote flame spread even when directly exposed to fire. Approved for use in many NFPA 285-compliant designs, Cavityrock® is an important component of fire-resilient exterior wall systems when used as a continuous insulation.

Cavityrock® also offers energy efficiency with reliable thermal performance, improved acoustic comfort, and is moisture resistant to maintain insulating value for the long-term.

Also available in a black mat facer finish for open-joint cladding systems, Cavityrock® Black combines your insulation install with masking in a single step, reducing installation time and material cost to achieve your desired design aesthetic.

Learn more at [rockwool.com/products/cavityrock/](https://rockwool.com/products/cavityrock/)

## Fire performance

Noncombustible, Cavityrock® can slow the spread of fire, and resists the transfer of heat in a wall assembly that causes layers on the other side to begin burning or smoking.



# Cavityrock®

## Exterior insulation for cavity wall and rainscreen applications

### Technical data sheet

Board Insulation 07210\* • Board Insulation 07 21 13\*\*  
Cavity Wall Unit Masonry 04 27 23\*\*

**ROCKWOOL Cavityrock® is a stone wool insulation board designed for exterior cavity wall and rainscreen applications. Compatible with numerous cladding attachment systems, Cavityrock® is noncombustible and available with a black mineral fleece facing for open-joint cladding systems.**

|  | Performance   | Test standard   |        |        |                               |                               |         |         |  |  |        |        |        |         |         |         |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |           |
|--|---|---|--------|--------|-------------------------------|-------------------------------|---------|---------|--|--|--------|--------|--------|---------|---------|---------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|-----------|
| Compliance                                   | Mineral fiber block and board thermal insulation - Type IVB compliant<br>Mineral fiber thermal insulation for buildings, Type 1 compliant<br>MEA approval, New York City approval   | ASTM C612<br>CAN/ULC S702<br>236 - 05 - M                                   |        |        |                               |                               |         |         |  |  |        |        |        |         |         |         |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |           |
| Reaction to fire                             | Flame spread index = 0; Smoke developed index = 0<br>Flame spread rating = 0; Smoke developed classification = 0<br>Combustibility of materials at 750 °C - Noncombustible<br>Determination of non-combustibility of building materials - Non-combustible   | ASTM E84 (UL 723) <sup>1</sup><br>CAN/ULC S102<br>ASTM E136<br>CAN/ULC S114 |        |        |                               |                               |         |         |  |  |        |        |        |         |         |         |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |           |
| Reaction to fire (with black mat facer)      | Flame spread index = 15; Smoke developed index = 0<br>Flame spread rating = 15; Smoke developed classification = 5  | ASTM E84 (UL 723)<br>CAN/ULC S102   |        |        |                               |                               |         |         |  |  |        |        |        |         |         |         |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |           |
| Monolithic density (thickness: 1", 1.5", 2") | > 4.3 lbs/ft <sup>3</sup> (>69 kg/m <sup>3</sup> ) <sup>†</sup><br><sup>†</sup> Density will change with thickness, please contact ROCKWOOL for more information  | ASTM C303   |        |        |                               |                               |         |         |  |  |        |        |        |         |         |         |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |           |
| Density (thickness ≥ 2.5")                   | Dual density - 6.2 lbs/ft <sup>3</sup> (100 kg/m <sup>3</sup> ) outer layer and 3.8 lbs/ft <sup>3</sup> (61 kg/m <sup>3</sup> ) inner layer   | ASTM C303   |        |        |                               |                               |         |         |  |  |        |        |        |         |         |         |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |           |
| Dimensional stability                        | Linear shrinkage = 0.1 % @ 1200 °F (649 °C)   | ASTM C356   |        |        |                               |                               |         |         |  |  |        |        |        |         |         |         |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |           |
| Corrosion resistance                         | Corrosiveness to aluminum - Passed<br>Corrosiveness to steel - Passed   | ASTM C665<br>ASTM C1617   |        |        |                               |                               |         |         |  |  |        |        |        |         |         |         |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |           |
| Thermal resistance                           | R-Value / inch @ 75 °F                      4.2 hr.ft <sup>2</sup> .F/Btu<br>RSI value / 25.4 mm @ 24 °C                0.74 m <sup>2</sup> K/W   | ASTM C518 (C177)  |        |        |                               |                               |         |         |  |  |        |        |        |         |         |         |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |           |
| Reaction to moisture                         | Water vapor sorption - 0.01 vol%<br>Water vapor transmission (2.48 in. thickness evaluated), desiccant method - 35 perm (2005 ng/Pa.s.m <sup>2</sup> )<br>Determination of fungi resistance - Passed  | ASTM C1104<br>ASTM E96<br>ASTM C1338  |        |        |                               |                               |         |         |  |  |        |        |        |         |         |         |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |           |
| Reaction to moisture (with black mat facer)  | Water vapor transmission (3.38 in. thickness evaluated), desiccant method - 43 perm (2435 ng/Pa.s.m <sup>2</sup> )<br>Determination of fungi resistance - Passed  | ASTM E96<br>ASTM C1338  |        |        |                               |                               |         |         |  |  |        |        |        |         |         |         |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |           |
| Dimensions                                   | Product is available in 1" (25.4 mm) to 6" (152.4 mm) in 1/2" increments, 7" (177.8 mm), 8" (203.2 mm)<br>24" x 48" (610 mm x 1219 mm) and 16" x 48" (406 mm x 1219 mm), with 32" x 48" (812.8 mm x 1219 mm)<br>available in 3", 4", 5" and 6" thicknesses  |   |        |        |                               |                               |         |         |  |  |        |        |        |         |         |         |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |           |
| Dimensions (with black mat facer)            | Product is available in 2" (50.8 mm) to 4" (101.6 mm) in 1/2" increments, 5" (127 mm), 6" (152.4 mm)<br>24" x 48" (610 mm x 1219 mm) and 16" x 48" (406 mm x 1219 mm), 5" (127 mm) and 6" (152.4 mm)<br>available only in 24" x 48" (610 mm x 1219 mm)  |   |        |        |                               |                               |         |         |  |  |        |        |        |         |         |         |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |           |
| Acoustical performance                       | <table border="1"> <thead> <tr> <th rowspan="2">Thickness</th> <th rowspan="2">NRC</th> <th rowspan="2">SAA</th> <th colspan="6">Sound absorption coefficients</th> </tr> <tr> <th>125 Hz</th> <th>250 Hz</th> <th>500 Hz</th> <th>1000 Hz</th> <th>2000 Hz</th> <th>4000 Hz</th> </tr> </thead> <tbody> <tr> <td>2.0"</td> <td>1.05</td> <td>1.04</td> <td>0.27</td> <td>0.76</td> <td>1.19</td> <td>1.13</td> <td>1.07</td> <td>1.04</td> </tr> <tr> <td>3.0"</td> <td>1.05</td> <td>1.06</td> <td>0.80</td> <td>1.04</td> <td>1.10</td> <td>1.03</td> <td>1.03</td> <td>1.04</td> </tr> <tr> <td>4.0"</td> <td>1.10</td> <td>1.12</td> <td>1.00</td> <td>1.15</td> <td>1.15</td> <td>1.08</td> <td>1.09</td> <td>1.08</td> </tr> <tr> <td>5.0"</td> <td>1.10</td> <td>1.09</td> <td>1.25</td> <td>1.08</td> <td>1.11</td> <td>1.06</td> <td>1.07</td> <td>1.05</td> </tr> <tr> <td>6.0"</td> <td>1.05</td> <td>1.03</td> <td>1.05</td> <td>0.95</td> <td>1.06</td> <td>1.07</td> <td>1.08</td> <td>1.05</td> </tr> </tbody> </table> | Thickness   | NRC    | SAA    | Sound absorption coefficients |                               |         |         |  |  | 125 Hz | 250 Hz | 500 Hz | 1000 Hz | 2000 Hz | 4000 Hz | 2.0" | 1.05 | 1.04 | 0.27 | 0.76 | 1.19 | 1.13 | 1.07 | 1.04 | 3.0" | 1.05 | 1.06 | 0.80 | 1.04 | 1.10 | 1.03 | 1.03 | 1.04 | 4.0" | 1.10 | 1.12 | 1.00 | 1.15 | 1.15 | 1.08 | 1.09 | 1.08 | 5.0" | 1.10 | 1.09 | 1.25 | 1.08 | 1.11 | 1.06 | 1.07 | 1.05 | 6.0" | 1.05 | 1.03 | 1.05 | 0.95 | 1.06 | 1.07 | 1.08 | 1.05 | ASTM C423 |
| Thickness                                    | NRC   |   |        |        | SAA                           | Sound absorption coefficients |         |         |  |  |        |        |        |         |         |         |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |           |
|  |   | 125 Hz  | 250 Hz | 500 Hz |                               | 1000 Hz                       | 2000 Hz | 4000 Hz |  |  |        |        |        |         |         |         |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |           |
| 2.0"   | 1.05  | 1.04  | 0.27   | 0.76   | 1.19                          | 1.13                          | 1.07    | 1.04    |  |  |        |        |        |         |         |         |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |           |
| 3.0"   | 1.05  | 1.06  | 0.80   | 1.04   | 1.10                          | 1.03                          | 1.03    | 1.04    |  |  |        |        |        |         |         |         |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |           |
| 4.0"   | 1.10  | 1.12  | 1.00   | 1.15   | 1.15                          | 1.08                          | 1.09    | 1.08    |  |  |        |        |        |         |         |         |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |           |
| 5.0"   | 1.10  | 1.09  | 1.25   | 1.08   | 1.11                          | 1.06                          | 1.07    | 1.05    |  |  |        |        |        |         |         |         |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |           |
| 6.0"   | 1.05  | 1.03  | 1.05   | 0.95   | 1.06                          | 1.07                          | 1.08    | 1.05    |  |  |        |        |        |         |         |         |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |           |
| UV stability (with black mat facer)          | Determination of changes in color fastness: achieved rating of 5/5 at 250 hr. and 500 hr. exposure, no perceptible change in color, and a rating of 4/5 at 750 hr. and 1,000 hr. exposure.  | ISO 105-AO2: 1993   |        |        |                               |                               |         |         |  |  |        |        |        |         |         |         |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |           |

Issued: 04-2026  
Supersedes 08-2025

Declare.



<sup>1</sup> Meets Class A requirements for flame spread and smoke-developed indices as per IBC  
\* Master Format 1995 Edition \*\* Master Format 2004 Edition.

As ROCKWOOL has no control over installation design and workmanship, accessory materials or application conditions, ROCKWOOL does not warranty the performance or results of any installation containing ROCKWOOL's products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty is in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. Sustainability certifications may vary by product and region.



8024 Esquesing Line, Milton, ON L9T 6W3  
Tel: 800-265-6878 • Fax: 800-991-0110  
rockwool.com