

ProRox® WM 950^{ES}

ProRox WM 950^{ES} is a lightly bonded stone wool insulation mat stitched on galvanized wire mesh with galvanized wire. Stainless steel mesh and binding wire (SW) is available upon request. The wired mats are produced with an innovative water-repellent binder, known as WR-Tech™, to mitigate the risk of corrosion under insulation (CUI). WR-Tech ensures our stone wool maintains its superior water repellency even at elevated operating temperatures within the CUI range, while preserving its excellent thermal performance in use.



Application

The wired mat is suitable for the thermal and acoustic insulation of industrial installations exposed to the environment, such as outdoor industrial pipework and equipment at petrochemical plants and refineries.



Product properties

Properties	Performance												Norms
	T (°C)	50	100	150	200	250	300	350	400	500	600	640	
Thermal conductivity	λ (W/mK)	0,039	0,045	0,053	0,062	0,072	0,084	0,097	0,112	0,146	0,192	0,213	EN 12667
Maximum Service Temperature	640°C												EN 14706
Reaction to fire	Euroclass A1												EN 13501-1
Density	80 kg/m ³												EN 1602
Corrosion resistance	Trace quantity of water leachable chloride ions: ≤ 10 ppm												EN 13468
Water absorption	$\leq 0,2$ kg/m ² $\leq 0,2$ kg/m ² (After 24 hrs. pre-heating at 250°C)												EN 1609 EN ISO 29767
Water vapour diffusion resistance	$\mu = 1$												EN 14303
EN 14303 Designation code*	MW EN 14303-T2-ST(+)-640-WS1-CL10												EN 14303

* Thickness class declared under the load of 1000 Pa

Compliance

- ProRox WM 950^{ES} fully complies with the requirements as set by the internationally recognized standards like EN 14303.

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.

ROCKWOOL® Technical Insulation, ROCKWOOL®, SeaRox® and ProRox® are registered trademarks of ROCKWOOL A/S and cannot be used without a prior written consent.